



DESCRIPTION

Cervac Board C-80 is a rigid product made from high alumina Fiberfrax® Ceramic Fibre. Boards are vacuum formed from fibre containing slurry with organic & inorganic binders and mineral fillers. These are manufactured over a wide range of sizes & thicknesses.

These boards may be used as individual components of very high temperature (>1300°C) furnace linings or as hard hot face layer for Durablankets.

GENERAL CHARACTERISTICS

Cervac Board C-80 has the following outstanding characteristics :

- High temperature stability (>1300°C)
- Low thermal conductivity & heat storage
- Highly resistance to thermal shock
- Resistance to erosion
- Easy to cut / machine with standard tools

TYPICAL APPLICATIONS

- High temperature furnace and kiln linings
- Hot gas duct liner
- Trough liners & covers

Any new and/or special use of these products, whether or not in an application listed in our literature, must be submitted to our technical department for their prior written approval.

*greener
cleaner
safer*
specialty fibers for
a greener, cleaner, safer world

Unifrax India Private Limited (Formerly Unifrax India Limited)

C-102, Business Square, Andheri-Kurla Road, Andheri (East), Mumbai-400 093

T:+91 (22) 2921 2200 / 201 | F:+91 (22) 2921 2249 | unifrax.mumbai@unifrax.com | www.unifrax.com

UNIFRAX

TYPICAL PRODUCT PARAMETERS

Cervac Board		C-80	
Typical Chemical Analysis (fibre wt. %)			
Al_2O_3		68 - 72	
SiO_2		28 - 31	
$Fe_2O_3 + TiO_2$		< 0.2	
Others		< 0.2	
Loss on ignition (wt. %)		3 - 4	
Physical Properties			
Classification Temperature ($^{\circ}C$)		1600	
Density (kg/m^3)		> 576	
Hardness Shore Scale (min.)		50	
Flexural Strength (kg/cm^2)	Typ.	14	
	Spec.	10.5	
Compressive Strength (kg/cm^2)	Typ.	10% Comp.	5
		25% Comp.	10.5
	Spec.	10% Comp.	3.5
		25% Comp.	8.5

The above strengths are for thickness upto 25mm, for higher thickness the strength will be lower.

Thermal Conductivity (W/mK)

Mean Temp.

250 $^{\circ}C$	0.11
550 $^{\circ}C$	0.13
850 $^{\circ}C$	0.16
1000 $^{\circ}C$	0.21

Thermal Conductivity figures are empirical values (average) based on experience.

Permanent Linear Shrinkage (%) 24 Hour Soak

Temp.

1500 $^{\circ}C$	1.5
1600 $^{\circ}C$	2

For specification add 0.5% to above shrinkage value.

AVAILABILITY

Thickness (mm)	Pieces per Carton	
	Size : 500 x 1000 & 600 x 900	
6	14	
12	8	
19	5	
25	4	
38	3	
50	2	

Other thicknesses / sizes may be available on request subject to minimum order requirement.

HANDLING INFORMATION

A Material Safety Data Sheet has been issued describing the health, safety and environmental properties of this product, identifying the potential hazards and giving advice on handling precautions and emergency procedures. This must be consulted and fully understood before handling, storage or use.

Supplied by:

Classification temperature refers to the maximum short term temperature limit. The maximum continuous use limit depends upon application conditions. For certain applications continuous use temperature limits may be significantly reduced. For assistance or clarification please contact your nearest Unifrax Engineering office.

Information contained in this publication is for illustrative purposes only and is not intended to create any contractual obligation. Further information and advice on specific details of the products described should be obtained in writing from a Unifrax Corporation company (Unifrax India). Unifrax maintains a continuous programme of product development and reserves the right to change product specifications without prior notice. Therefore, it maintains at all times the responsibility of the customer to ensure that Unifrax materials are suitable for the particular purpose intended. Similarly, insofar as materials not manufactured nor supplied by Unifrax are used in conjunction with or instead of Unifrax materials, the customer should ensure that all technical data and other information relating to such materials has been obtained from the manufacturer or supplier. Unifrax accepts no liability arising from the use of such materials. All sales made by a Unifrax Corporation company are subject to that company's Terms and Conditions of Sale, copies of which are available on request.